Unilin bvba, division panels
Ingelmunstersteenweg 229, 8780 Oostrozebeke, Belgium
T: +32 56 66 70 21 - F : +32 56 66 82 25
info.panels@unilin.com - www.unilin.com

DECLARATION OF PERFORMANCE	
Reference :	DOPFibroMaxv2
Commercial name :	FibroMax
Product type :	MDF Fibreboard
Reference standard :	Wood Based Panel - EN13986:2004+A1:2015 Annex A Table A.9
CE Class :	MDF
Field of application :	Internal use as non-structural component in dry conditions
AVCP Class :	4
Certification number:	Not Applicable
Produced at:	Zone Industrielle, F-08140 Bazeilles
	Rue de la Forêt 2, B-6690 Vielsalm

Essential Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>12-19	>19-30	>30-45
Bending strength	N/mm²	EN 622-5	23	23	22	20	18	NPD
Modulus of elasticity in bending	N/mm²	EN 622-5	2700	2700	2500	2200	2100	NPD
Internal bond	N/mm²	EN 622-5	0,65	0,65	0,60	0,55	0,55	NPD
Swelling in thickness, 24h	%	EN 622-5	30	17	15	12	10	NPD
Moisture resistance OPTION 1 : Internal bond	N/mm²	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Moisture resistance OPTION 1 : Swelling in thickness	%	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Surface Soundness	N/mm²	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Formaldehyde class	Class	EN 13986-table B1	E1	E1	E1	E1	E1	NPD
Reaction to fire	Class	EN 13501-1	E	D-s2d0(*)	D-s2d0	D-s2d0	D-s2d0	NPD
Water vapour permeability μ	wet	EN 13986 - table 9	20	19	18	17	17	NPD
	dry		30	29	27	26	26	NPD
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	NPD	NPD	NPD	NPD
Sound absorption α		EN 13986 - table 10	0,10/0,20	0,10/0,20	0,10/0,20	0,10/0,20	0,10/0,20	NPD
Thermal conductivity λ	W/m.K	EN 13986 - table 11	0,14	0,14	0,13	0,13	0,12	NPD
Strength - tension ft	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - compression fc	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - bending f_m	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - panel shear f_v	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - planar shear f_r	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stifness - tension E_t	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stifness - compression E_c	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stifness - bending E_m	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stifness - panel shear G_v	N/mm²	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Impact resistance	Class	EN 12871	NPD	NPD	NPD	NPD	NPD	NPD
Punshing shear strength R_{mean}	N/mm²	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punshing shear strength $F_{ser,k}$	N/mm²	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punshing shear strength $F_{max,k}$	N/mm²	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Linear expansion $\delta l_{30,85}$	mm/m	EN 318	NPD	NPD	NPD	NPD	NPD	NPD
Mechanical durability (kmod; kdef)		Shall be taken from :	NPD	NPD	NPD	NPD	NPD	NPD
Biological durability	Service Class	EN 335	1	1	1	1	1	NPD
Content of PCP	ppm	EN 13986-5.18	<5	<5	<5	<5	<5	NPD

(*) <9mm : E; 9mm : D-s2,d0

Informative Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>12-19	>19-30	>30-45
Formaldehyde content	mg/100g	EN 120	< 8 mg/100g DS					

Version date :
6/05/2019

Lode De Boe,
President UNILIN bvba, division panels

